

PRODUCT SPECIFICATION

5017 Block

Binder	Polymeric
Colour	Black
Cork Granule Size	0.5/1 mm

TEST METHOD	PROPERTY	UNIT	VALUE
ASTM F 1315	Density	Kg/m ³	800
ASTM D 2240	Hardness	Shore A	60-80
ASTM F 36	Compressibility at 400 psi	%	20-40
ASTM F 36	Recovery	%	> 80
ASTM F 152	Tensile Strength (min)	MPa	1,22
ASTM F 147	Flexibility		
	Original (F=5)	-	No cracks
DIN EN ISO 1856	Compression Set - 70h, 50%, RT máx	%	15
ISO 8301	Thermal Conductivity*	W/m ^o K	0.177

* indicative value

PDA-00082/3